


ATOMIC

Sparkle

UNIQUE GLITTER FLEX


11 NEW
SPARKLY COLORS
FOR YOUR BRILLANT
DESIGNS




Red Sparkle 02




Orange Sparkle 03




Green Sparkle 04




Blue Sparkle 05



Purple Sparkle 06




Cherry Sparkle 07




Gold Sparkle 08



Silver Sparkle 09



White Sparkle 10



Black Sparkle 11

100% Polyurethane film
HIGH DURABILITY AND THE TRUSTED
SEF EASY CUTTING
& WEEDING



ATOMIC

Sparkle

UNIQUE GLITTER FLEX

1



Scan or create a digital vector image.

2



Cut a mirror-image of your design on a plotter-cutting machine.

3



Apply with an heat press.



OVERLAY GLITTER FLEX
SUPER EASY WEEDING
LIGHT AND SOFT

Atomic Sparkle

Transfer Temperature	Transfer Time	Transfer Pressure
150°C (300°F)	12 seconds	High pressure


Cotton, Polyester, PolyCotton...

Hot peel

Washing : up to 60°C (140°F)

Thickness : 150 µ

PACKAGING



50 cm (19,7")	5 meters (5,45yd)
50 cm (19,7")	10 meters (10,9yd)
50 cm (19,7")	25 meters (27,3yd)



110 Bd Denis-Papin - 53000 LAVAL - France
Tél: 33 (0)2 43 53 36 48
Fax : 33 (0)2 43 67 11 78
Email: contact@sef-france.com
www.seftextile.com



SEF AMERICAS
14476 DuvalPlace West /Ste.201
Jacksonville, FL 32218 /904-423-0211-Phone /USA
sales@SEFamericas.com
www.sefamericas.com